



Bumper & Trim Paint

James Briggs Ltd
Salmon Fields, Royton, Oldham OL2 6HZ UK
Tel: 0161 627 0101 Fax: 0161 627 0971
www.jamesbriggs.co.uk

1. Introduction

These products are designed for use on automotive bumpers and other forms of polymeric trim.

ATOBTDG500 624 AUTO TEK DARK GREY BUMPER & TRIM PAINT 500ML
ATOBTB500 617 AUTO TEK BLACK BUMPER & TRIM PAINT 500ML

2. Where to use

On rigid, non-porous plastics used in automotive construction.

3. Where not to use

- On flexible substrates

4. Benefits

- Excellent durability
- Excellent covering power
- Good resilience
- Excellent resistance to sunlight and colour fade.

5. Physical properties [Bumper paint bases except where stated].

Appearance	Coloured liquids with characteristic paint odours
pH	Not applicable
Specific Gravity	0.89 – 0.97
Viscosity	Low viscosity pourable liquids
Non Volatiles % m/m	40 - 50
Active Content % m/m, as supplied	10 – 20
Flammability, as supplied	Extremely Flammable, flash point below -20°C
Composition Data, as supplied	A solvent based solution of acrylic and other resins containing a range of pigments, plasticisers, and thixotropes, dispersed in a butane/propane/isobutane based propellant.
Volatile Organic Content as supplied	Compliant with EU Directive 2004/42/CE
Service Temperatures	Up to 80°C
Application Temperatures	15 - 25°C

6. Application Details

For best results, an application of an Adhesion Aid, is recommended

Prepare the area to be treated, ensuring freedom from dust, grime, greases, oils etc by wiping with a cloth damped with white spirit. Allow to dry.

Shake the can thoroughly for at least two minutes. Repeat shaking at regular intervals during use.

This information is provided in good faith based upon data and sources believed to be reliable and correct. Conditions of use, outside the control of the Company, dictate that no responsibility can be assumed for the ultimate performance of this product.



TECHNICAL DATA SHEET

Bumper & Trim Paint

James Briggs Ltd

Salmon Fields, Royton, Oldham OL2 6HZ UK

Tel: 0161 627 0101 Fax: 0161 627 0971

www.jamesbriggs.co.uk

Apply sparingly from a distance of 20 – 25cm. Apply 2 to 3 light coats as necessary to achieve total and even coverage, leaving at least 15 minutes between each application.

Allow to dry for 24 hours to develop maximum paint hardness.

On completion of use, invert can and depress actuator for a few seconds to prevent nozzle blockage.

7. Availability

500ml aerosols.

B049591/49593, RJB July 2013.