



TECHNICAL DATA SHEET

**ENGINE ENAMEL GLOSS
BLACK**

ATOOEEB500

James Briggs Ltd
Salmon Fields, Royton, Oldham OL2 6HZ UK
Tel: 0161 627 0101 Fax: 0161 627 0971
www.jamesbriggs.co.uk

1. Introduction

A heat resistant coating designed to enhance the appearance of automotive engines and to provide protection against corrosion.

2. Where to use

Primarily for use on engine blocks and cylinder heads

3. Where not to use

- On applications where the high temperature attributes are not required
- On surfaces where subsequent overcoating with an alternative coating is required.

4. Benefits

- One step application, products are self priming
- Excellent heat resistance*
- Extreme durability and toughness
- Resistant to petrol oils and greases

5. Physical properties [Engine Enamel bases except where stated].

Appearance	Coloured liquids with characteristic paint solvent odours.
pH	Not applicable
Specific Gravity	0.9 – 1.1
Viscosity	Pourable liquids
Non Volatiles % m/m	30 - 55
Active Content % m/m, as supplied	5.0 – 20.0
Flammability, as supplied	Extremely Flammable, flash point below -20°C
Composition Data, as supplied	Solvent based solutions of modified silicone and alkyd resins containing temperature stable pigment dispersions.
Volatile Organic Content as supplied	Compliant with EU Directive 2004/42/CE
Maximum Service Temperatures	Aluminium 300°C* Gloss Black 140°C Matt Black 300°C*
Application Temperatures	15 - 25°C

6. Application Details

Prepare the area to be treated, ensuring freedom from dust, grime, traffic film, greases, waxes, oils etc, using a detergent solution or an emulsifiable solvent based cleaner, followed by rinsing thoroughly and drying. Rust, other surface contamination, and loosely adhering matter should be removed using a wire brush or an appropriate grade of wet and dry abrasive paper.

Following preparation the surfaces should be further treated with a solvent wipe, white spirit, or thinners and allowed to dry.

Shake the can thoroughly for at least two minutes. Repeat shaking at regular intervals during use.

This information is provided in good faith based upon data and sources believed to be reliable and correct. Conditions of use, outside the control of the Company, dictate that no responsibility can be assumed for the ultimate performance of this product.



TECHNICAL DATA SHEET

**ENGINE ENAMEL GLOSS
BLACK**

ATOOEEB500

James Briggs Ltd
Salmon Fields, Royton, Oldham OL2 6HZ UK
Tel: 0161 627 0101 Fax: 0161 627 0971
www.jamesbriggs.co.uk

Do not use any primers.

Apply sparingly from a distance of 20 – 25cm. Apply a minimum of two coats or as necessary to achieve total and even coverage, leaving between 20 to 30 minutes between each application.

These products may be further overcoated with the same paints after a drying time of 24 hours.

On completion of use, invert can and depress actuator for a few seconds to prevent nozzle blockage.

* Optimum thermal stability, durability, and chemical resistance for the two asterisked products will be achieved following post application heat curing at 220°C.

7. Availability

500ml aerosols.

PNT423 RJB July 2013.