



ETCH PRIMER

James Briggs a division of ITW Ltd
Salmon Fields, Royton, Oldham OL2 6HZ UK
Tel: 0161 627 0101 Fax: 0161 627 0971
www.jamesbriggs.co.uk

ATOOOEP500

1. Introduction

A grey modified acrylic primer based upon a speciality resin designed primarily to key onto non-ferrous metals, and to provide a tough, durable coating suitable for subsequent application of the Autotek range of standard gloss, satin and matt finishes, and acrylic coloured paints.

2. Where to use

On non-ferrous metals including galvanised, anodised and zinc coated steel, aluminium.

3. Where not to use

- Not recommended for use on copper or brass

4. Benefits

- Excellent covering power
- Excellent adhesion to most non-ferrous surfaces.
- Suitable for use on many rigid plastics including glass reinforced polyester [See Section 6].
- Suitable for use on fully cured and aged paint finishes [See Section 6].

5. Physical properties [Etch Primer base except where stated].

Appearance	Grey liquid with a characteristic paint solvent odour.
pH	Not applicable
Specific Gravity	1.20 – 1.25
Viscosity	500 – 1,500cPs
Non Volatiles % m/m	40 -50
Active Content % m/m, as supplied	15 - 20
Flammability, as supplied	Extremely Flammable, flash point below -20°C
Composition Data, as supplied	A solvent based solution of a modified acrylic resin containing pigments, extenders, plasticizer, thixotropes and wetting agents dispersed in a butane/propane/isobutane based propellant.
Volatile Organic Content as supplied	Compliant with EU Directive 2004/42/CE
Service Temperatures	Up to 80°C
Application Temperatures	15 - 25°C

6. Application Details

Prepare the area to be treated, ensuring freedom from dust, grime, greases, oils etc, using a detergent solution followed by rinsing thoroughly and drying. Any corrosion, other surface contamination, and loosely adhering matter should be removed with an appropriate grade of wet and dry abrasive cloth. Following preparation the surfaces should be further treated with a solvent wipe, white spirit, or thinners and allowed to dry.

If in doubt about the composition of the substrate, undertake a small test application on an inconspicuous area prior to use to ensure suitability.

This information is provided in good faith based upon data and sources believed to be reliable and correct. Conditions of use, outside the control of the Company, dictate that no responsibility can be assumed for the ultimate performance of this product.



TECHNICAL DATA SHEET

ETCH PRIMER

James Briggs a division of ITW Ltd
Salmon Fields, Royton, Oldham OL2 6HZ UK
Tel: 0161 627 0101 Fax: 0161 627 0971
www.jamesbriggs.co.uk

ATOOOEP500

Shake the can thoroughly for at least two minutes. Repeat shaking at regular intervals during use.

Apply sparingly from a distance of 20 – 25cm. Apply 2 to 3 light coats to achieve total and even coverage, leaving at least 15 minutes between each application.

Allow at least 24 hours between application of final coating and preparation for any subsequent finishes that may be required.

On completion of use, invert can and depress actuator for a few seconds to prevent nozzle blockage.

7. Availability

500 ml aerosols.

B047179 ,RJB, July 2013.