



STONEGUARD

James Briggs Ltd
Salmon Fields, Royton, Oldham OL2 6HZ UK
Tel: 0161 627 0101 Fax: 0161 627 0971
www.jamesbriggs.co.uk

1. Introduction

A range of high quality rubberised coatings designed to provide body panel protection from physical traffic induced damage.

ATOOSGB500 532 AUTO TEK STONEGUARD BLACK 500ML

ATOOSGG500 549 AUTO TEK STONEGUARD GREY 500ML

ATOOSGW500 556 AUTO TEK STONEGUARD WHITE 500ML

2. Where to use

Lower body panels including sills and valences.

3. Where not to use

- This product is a specific rubberised coating, and should be used only for the intended application.

4. Benefits

- Protection against stone chip damage
- Protection against paint cracking and scratching
- Prevention of corrosion

5. Physical properties [Stoneguard bases except where stated].

Appearance	Black, white or grey viscous liquids.
pH	Not applicable
Specific Gravity	0.97 – 1.10
Viscosity	5,500 cPs maximum
Non Volatiles % m/m	35 - 45
Active Content % m/m, as supplied	20 - 30
Flammability, as supplied	Extremely flammable, flash point below -20°C
Composition Data, as supplied	A solution of a styrenated rubber and hydrocarbon resins in a blend of solvents. Other components include plasticizers, pigments and extenders, thixotropes and wetting agents, dispersed in a butane/propane/isobutane based propellant.
Volatile Organic Content, as supplied	Compliant with EU Directive 2004/42/CE
Service Temperatures	Up to 80°C.
Application Temperatures	10 - 25°C

6. Application Details

Ensure surfaces are clean, dry, and free from oils, traffic film, greases, tars etc. If necessary, wash the surface with a good quality detergent rinse thoroughly and dry with a cloth. Wipe over the surface with white spirit, to remove any tar or asphalt deposits, and allow to dry. Mask the area to prevent overspray. Undertake a small test application on an inconspicuous area prior to use to ensure suitability for use.

Shake the can thoroughly for at least two minutes. Repeat shaking at regular intervals during use.

Apply sparingly from a distance of 20 – 25cm to avoid runs. Apply typically 2 to 3 coats or as necessary to achieve total and even coverage, leaving at least 15 minutes between each application.

This information is provided in good faith based upon data and sources believed to be reliable and correct. Conditions of use, outside the control of the Company, dictate that no responsibility can be assumed for the ultimate performance of this product.



TECHNICAL DATA SHEET

STONEGUARD

James Briggs Ltd
Salmon Fields, Royton, Oldham OL2 6HZ UK
Tel: 0161 627 0101 Fax: 0161 627 0971
www.jamesbriggs.co.uk

Allow at least 24 hours between application of final coating and any subsequent finishes that may be required.

On completion of use, invert can and depress actuator for a few seconds to prevent nozzle blockage.

7. Availability

500ml aerosols.

B069360/3/4F RJB July 2013 .